

PAVIMENTO INDUSTRIAL INDUSTRIAL FLOORING



Ancho Width	Largo Length	Espesor Thickness	Peso / unidad Weight / unit
120 mm.	245 mm.	14 mm. 17 mm. 19 mm.	0,80 kg. 1,05 kg. 1,20 kg.

CARACTERÍSTICAS TÉCNICAS / TECHNICAL DATA ISO 13006 - EN 14411

CARACTERÍSTICAS TÉCNICAS TECHNICAL CHARACTERISTICS		NORMATIVA EN 14411 ISO 13006	KLINKERTECH 14 MM A1a	KLINKERTECH 17 MM A1a	KLINKERTECH 19 MM A1a
ISO 10545-2	Características dimensionales Dimensions and surface quality	Exigida Required	Cumple Passed	Cumple Passed	Cumple Passed
ISO 10545-3	 Absorción de agua Water absorption	Grupo A1a <0.5%	E ≤0.2 %	E ≤0.2 %	E ≤0.2 %
ISO 10545-4	 Fuerza de rotura Breaking strength	≥1.300 N	≥3.600 N	≥6.900 N	≥7.400 N
	 Resistencia a la flexión Bending resistance	≥ 28 N/mm ²	> 40 N/mm ²	> 40 N/mm ²	> 40 N/mm ²
ISO 10545-6	 Resistencia a la abrasión profunda de baldosas no esmaltadas Resistance to deep abrasion natural tiles	≤ 275mm ³	≤150mm ³	≤150mm ³	≤150mm ³
ISO 10545-9	 Resistencia al choque térmico Thermal shock resistance	Exigida Required	Garantizada Guaranteed	Garantizada Guaranteed	Garantizada Guaranteed
ISO 10545-12	 Resistencia a la helada Frost resistance	Exigida Required	Garantizada Guaranteed	Garantizada Guaranteed	Garantizada Guaranteed
ISO 10545-13	 Resistencia química Chemical resistance	Mínimo UB (natural)	UA ULA UHA	UA ULA UHA	UA ULA UHA
ISO 10545-14	 Resistencia a las manchas Stain resistance	Mínimo clase 3	Garantizada Guaranteed	Garantizada Guaranteed	Garantizada Guaranteed

SEGURIDAD / SAFETY		DESCRIPCIÓN DESCRIPTION	Coefficientes Antideslizamiento Resultados Non-slip coefficients Results
DIN 51130		Norma para pie calzado Norm for shoe traffic areas	R11

ISO 22196
ISO 21702



Gres extrusionado **antibacteriano y antivírico**
Antibacterial and antiviral extruder clinker